



**Metaltec
Steel
Abrasive Co.®**

CAST STEEL GRIT HARDNESS RANGES

GET THE RIGHT HARDNESS FOR YOUR BLASTING APPLICATION

GS	40-51 HRC
GM	47-56 HRC
GL	54-61 HRC
GH	60 + HRC

- **GS – STANDARD HARDNESS GRIT** – SAFE FOR USE IN CENTRIFUGAL WHEEL MACHINES. WEAR CHARACTERISTICS ARE SIMILAR TO STEEL SHOT. TYPICALLY NOT SUITED FOR AIR BLAST APPLICATIONS.
- **GM – MEDIUM HARDNESS GRIT** – MORE AGGRESSIVE THAN GS HARDNESS, THIS CAN BE USED IN BOTH AIR AND WHEEL BLASTING APPLICATIONS.
- **GL – HARD GRIT** – PROVIDES A GOOD BALANCE OF CLEANING, SPEED, AND DURABILITY - EXCELLENT FOR AIR BLAST APPLICATIONS.
- **GH – FULL HARD GRIT** – MOST AGGRESSIVE MEDIA WITH NO ROUNDING CHARACTERISTICS - PROVIDES FAST CLEANING AND SURFACE PREPARATION. USED FOR FAST AGGRESSIVE CUTTING, STONE WORK, HEAVY SCALE REMOVAL, EPOXY CUTTING, ETC.



**METALTEC USES THE ENTIRE
CASTING DISTRIBUTION TO
PRODUCE HIGH DENSITY
AGGRESSIVE GRIT.**

41155 Joy Road, Canton MI 48187
Phone: 734-459-7900 Fax: 734-459-7907

metaltecsteel.com